

Thermal Lamination Film Nylon Velvet

PCT-2(NDL) VT

Description

It is Nylon based, one side velvet feel matte coated and other side extrusion coated, both sides treated thermal laminating film. Film has extrusion coated surface with low temp. melting resin, which enables the lamination of film to paper products by heat and pressure.

Features

- Rich velvet feel
- Good resistance to Scuff
- Excellent lay flat property (prevent curl under humid conditions)
- Natural matte finish
- Good hot stamping & UV laquer adhesion
- Fibre-tear bond strength with paper

Applications

- Thermal lamination with all kinds of printed & unprinted paper and paper boards like maps, menu cards, certificates, mark sheets, folders, photo albums, posters, magazines, brochures etc.

Special Instruction

- Cosmo nylon based velvet touch thermal matte film can be laminated with the temperature range of 120 to 135 deg C. However the optimum conditions may be selected based on the lamination speed (Dwell time) and dimensional stability.
- Please make sure that the printed surface is well dried before lamination
- Strongly recommend to handle with care and cleanliness as it may spoil it's look by rough handling, dust contamination and scratches.
- It is advisable to cool sufficiently one surface before proceeding the lamination to
- other surface.

Typical values

Properties	Ref.	Units	ASTM#/ Test Method	PCT-2(NDL) VT
Physical Data				
Average Thickness		Micron		35
		Gauge		140
		Mils		1.4
Average substance		g/m²		34.5
Yield		m²/Kg	D-4321	29.0
		in²/lb		20389
Surface Tension(min)	Matte Side	dynes/cm	D-2578	36
	Ex-coated Side			50
Optical Data				
Gloss (45°)	Matte	Gardner	D-2457	5-6
Thermal Data				
Lamination Temperature		°C	D-1204	120-135
		°F		248-275

CTM : Cosmo Test Method

MD : Machine Direction

TD : Transverse Direction

Disclaimer : The information provided above is based on COSMO FILMS LTD's conclusive tests, which are indicative only and provided as guidelines. They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications

Storage condition : Storage temperature to be maintained 25 Deg.C (+/-5 Deg C) & relative humidity 55% (+/-5%) to avoid accelerated reduction of surface treatment level.

Cosmo Films Limited

1st Floor, Uppal's Plaza, M-6 Jasola District Centre, New Delhi - 110025, India, T: + 91-11-49 49 49 49,

E-mail: sales.enquiry@cosmofilms.com | www.cosmofilms.com

Create Date : 2022-Aug-25