Synthetic Paper Matte, Non Coated, Roll/Sheet Form

CSPR-2 (M) / CSPS-2 (M)

Description

It is a co-extruded, white opaque, both sides corona treated polypropylene based film which resembles paper in appearance

Features

- Non tearable
- Moisture resistance
- Oil and chemical resistance
- Dimensionally stable
- Excellent printability
- Excellent folding endurance
- Recyclable
- Superior tensile and tear strength
- Writeable with pencils and oil-based pens
- Printable by Conventional offset and Screen printing processes
- Can be folded, sheeted, stapled, hot foil stamped, die – punched, serrated, adhesive bonded and perforated (for perforation always keep tie length ≤ 0.5 mm & edges of perforated sheet or label should be cut)

Applications

- Commercial Printing maps, calendars, brochures, Menu cards , flip charts, children books
- Tags and Labels garment tags, baggage tags, Glass bottle labels, food labels, horticulture labels
- Retail & Packaging POP graphics, posters, danglers, indoor billboards, banners, backlit displays
- Identification & Credentials visiting cards, identity Cards, marksheets & certificates, legal documents
- Outdoor outdoor billboards, frontlit & backlit Displays, train station & airport signages

| | | | | | | | | / | _ ı y | זונמו | vall | 162 | |
|-------------------------|--------------|--------------------|-------------------------|--|--------|---------|-------|-------|-------|-------|-------|-------|-------|
| Properties | Ref. | Units | Astm # / Test Method | CSPR-2 (M) / CSPS-2 (M) | | | | | | | | | |
| Physical Data | | | | | | | | | | | | | |
| | | micron | | 95 | 120 | 150 | 175 | 195 | 215 | 275 | 330 | 375 | 430 |
| Average Thickness | | Gauge | D-374-C | 380 | 480 | 600 | 700 | 780 | 860 | 1100 | 1320 | 1500 | 1720 |
| | | Mills | | 3.8 | 4.8 | 6.0 | 7.0 | 7.8 | 8.6 | 11.0 | 13.2 | 15.0 | 17.2 |
| Average Substance | | g/m² | | 69.0 | 88.0 | 106.0 | 127.0 | 140.0 | 155.0 | 202.0 | 231.0 | 266.0 | 305.0 |
| Thickness Variation | | % (<u>+</u>) | | 5 | | | | | | | | | |
| Surface Tension (min) | Both Side | dynes/cm | D-2578 | >38 | | | | | | | | | |
| Yield | | m²/Kg | D-4321 | 14.4 | 11.3 | 9.4 | 7.8 | 7.1 | 6.4 | 5.0 | 4.3 | 3.7 | 3.2 |
| | | | | Optic | al Dat | a | | | | | | • | |
| Gloss (45 °) | | gardner | D-2457 | 10 | | | 10 | | | | | | |
| Opacity | | % | Hunter Lab D25 - 2CR | 70-75 90 93 95 | | | | | | | | | |
| Whiteness Index | | % | E-313 | 92 94 | | | | | | | | | |
| | | • | Μ | echan | ical D | ata | ' | | | | | | |
| Tensile Strength | MD TD | kg/cm ² | D-882 | 550 - 650 1100 - 1400 | | | | | | | | | |
| Elongation | MD TD | kg/cm ² | D-882 | 550 - 650 1100 - 1400 130 - 180 20 - 40 | | | | | | | | | |
| CTM : Coomo Toot Mothod | | | | | TD . | Tropovo | Dime | | | | | | |

CTM : Cosmo Test Method

MD : Machine Direction

TD : Transverse Direction

Typical Values

Disclaimer : The information provided above is based on COSMO FILMS LTD's conclusive tests, which are indicative only and provided as guidelines. They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.

Cosmo Films Limited

B-14/8-9, MIDC Industrial Area, Waluj, Aurangabad - 431 136, India, T: +91 240 6660000, 1008,DLF Tower -A, Jasola District Centre, New Delhi - 110 025, India, T: + 91-11-49 49 49 49, E-mail: sales.enguiry@cosmofilms.com