# Thermal Lamination Film BOPP Silky Matte

27 PCT-2 (M-SIL) DL

### **Description**

It is BOPP based, one side silky matte and both side treated thermal laminating film. Film has extrusion coated surface with low temp. melting resin, which enables the lamination of film to paper products by heat and pressure.

Un-Coated

Lamination Temp.

Gloss (45°) - Un-Coated side

#### **Features**

- Silky satin finish
- Excellent resistance to elongation & tear
- Yellow tint free appearance of roll
- Fibre-tear bond strength with paper

# **Applications**

 Thermal lamination with all kinds of printed & unprinted paper and paper boards like book covers, posters, magazines, diaries, brochures, manuals, folders, magazines, photo albums etc.

## Special Instructions

17 - 25

100 - 120

- Cosmo thermal Silky Matte film can be laminated with the temperature range of 100 to 120 deg C. However the optimum conditions may be selected based on the lamination speed (Dwell time) and dimensional stability.
- Please make sure that the printed surface is well dried before lamination.
- Strongly recommend to handle with care and cleanliness as it may spoil it's look by rough handling, dust contamination and scratches.
- It is advisable to cool sufficiently one surface before proceeding the lamination to other surface.

#### ASTM # / Test 27 PCT-2 (M-SIL) DL **Properties** Units Method Unit Weight g/m<sup>2</sup> 22.5 Yield m²/ka D - 4321 44.4 Surface Tension (min.)-Ex-coated side dynes/cm D - 2578 40

gardner

**Typical Values** 

Disclaimer: The information provided above is based on COSMO FILMS LTD's conclusive tests, which are indicative only and provided as guidelines. They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.

D - 2457

D - 1204

#### Cosmo Films Limited